



## TECHNICAL PRODUCT INFORMATION

Product: Diffused thermic film with anti-fog for tunnels

Catalog Number: E1601

Product description: Multi-layer PE film. The anti-fog additives to prevent dripping onto the plants

and IR ingredient reduce heat "escape" at night.


UV Resistance: 1-2 Seasons Thickness:  $100-120 \mu$  Width: 1.0-14.5 m

Length: According to customer order

| rioperty                       |  |  |
|--------------------------------|--|--|
| Tensile Strength at break [MD] |  |  |
| Tensile Strength at break [TD] |  |  |
| Elongation at break [MD]       |  |  |
| Elongation at break [TD]       |  |  |
| Tear resistance [MD]           |  |  |
| Tear resistance [TD]           |  |  |
| Falling Dart Impact            |  |  |
| Total light transmission       |  |  |
| Light diffusion                |  |  |
| Thermicity                     |  |  |
| UV blocking                    |  |  |
| Thickness average              |  |  |
| Thickness tolerance            |  |  |

Dronarty

| Test Method      | Units  | Value          |
|------------------|--------|----------------|
| ASTM D-882       | MPa.   | 18             |
| ASTM D-882       | MPa.   | 18             |
| ASTM D-882       | MPa.   | 500            |
| ASTM D-882       | MPa.   | 500            |
| ASTM D-1922      | Kg./mm | 7.0            |
| ASTM D-1922      | Kg./mm | 10             |
| ASTM D-1709      | gr.    | 800            |
| nternal          | %      | 90             |
| nternal          | %      | 50             |
| nternal (FTIR)   | %      | 80             |
| nternal          | %/nm   | NA             |
| sraeli Stnd. 821 | %      | ±5% on nominal |
| sraeli Stnd. 821 | %      | ±15%           |
|                  |        |                |



## Kibbutz Einat P.O.B 3 | Einat 4880500 Israel | Tel :+972-3-9016060 | Fax:+972-3-9016040

All statements, information and data given herein are believed to be accurate a reliable, but are presented without guaranty, warranty or responsibility any kind, express or limited. Statement or suggestion concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendation to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required