TECHNICAL PRODUCT INFORMATION

Product:	Brown TIF film
Catalog Number:	E1189
UV resistance:	10 months
Thickness:	32-40 µ
Width:	0.8-2.5 m
Length:	According to customer order

Product properties

Property	Test Method	Units	Value
Tensile Strength at break[MD]	ASTM D-882	MPa.	22
Tensile Strength at break[TD]	ASTM D-882	MPa.	22
Elongation at break [MD]	ASTM D-882	%	300 min
Elongation at break [TD]	ASTM D-882	%	300 min
Total light transmission	EN 13206	%	Max 4%
Permeability for Fumigation by DMDS (40^0C, 100%RH)-MTC		Cm/hour	0.21
Equilibrium temperature		hours	59
Thickness average	EN 13206	%	±5% on nominal
Thickness tolerance	EN 13206	%	±15%

All statements, information and data given herein are believed to be accurate a reliable, but are presented without guaranty and warranty or responsibility any kind, express or limited. Statement or suggestion concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendation to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required

P.O. Box 3, Kibutz Einat 4880500 Israel politiv@politiv.co.il
+972-3-9016060 +972-3-9016040 www.politiv.co.il