TECHNICAL PRODUCT INFORMATION

Product:	Milky Diffused Thermic Anti-Dust with 25% shade.
Catalog Number:	E1835
Product description:	Multi-layer greenhouse cover with 25% shade. The film contains special white pigment to reduce the light and heat transmission at day. The film contains also IR barrier to prevent heat escape at night. The film has high mechanical properties.
UV Resistance:	2 years
Thickness:	150-200 µ
Width:	Up to 18.0 m
Length:	According to customer order

Product properties

Property	Test Method	Units	Value
Tensile Strength at break [MD]	ASTM D-882	MPa.	27±10%
Tensile Strength at break [TD]	ASTM D-882	MPa.	27±10%
Elongation at break [MD]	ASTM D-882	%	600 min
Elongation at break [TD]	ASTM D-882	%	600 min
Tear resistance [MD]	ASTM D-1922	Kg./mm	10±10%
Tear resistance [TD]	ASTM D-1922	Kg./mm	11.0±10%
Falling Dart Impact (200 microns)	ASTM D-1709	gr.	1200 min
Total light transmission	E13206	%	68-70%
Light diffusion	E13206	%	60-70
Total light reflection	Internal	%	25±2%
Thermicity	E13206	%	65 min
UV blocking at 320-380 nm	E13206	%	83%
Thickness average tolerance	E13206	%	±5% on nominal

All statements, information and data given herein are believed to be accurate a reliable, but are presented without gua
warranty or responsibility any kind, express or limited. Statement or suggestion concerning possible use of our produc
without representation or warranty that any such use is free of patent infringement, and are not recommendation to
patent. The user should not assume that all safety measures are indicated, or that other measures may not be requir

P.O. Box 3, Kibutz Einat 4880500 Israel
+972-3-9016060 +972-3-9016040
politiv@politiv.co.il
www.politiv.co.il

Use and limitation:

- **Exposure to chemicals**: exposure of greenhouse films to severe chemical conditions has an adverse effect on the lifetime of the film. Avoid excessive use of agrochemicals such as pesticides, herbicides, fungicides and fertilizers. Take measures to prevent direct contact of chemicals to the film. Ensure that metal structures are galvanized and are free from corrosion. When wooden structure parts are used, avoid contact of the film with resin, oil, petroleum or volatile preservatives. Prevent contact of the film with PVC accessories. Chemicals containing halogens, sulfur, copper, iron, are known to accelerate the degradation of greenhouse films.

  Specifically, if the following elements are found at levels higher than specified, the films are excluded from this warranty:

  Sulfur: max 400 ppm, Chlorine: 40 ppm, Iron: 50 ppm

- **Overheating**: the film has an adverse effect on its lifetime. Hot air should be directed away from the film.

- **Disinfection chemical use**: when chemicals are used to disinfect the soil, the treated soil must be covered with a film for a minimum of three weeks. After the film is removed, the greenhouse should be ventilated.

All statements, information and data given herein are believed to be accurate a reliable, but are presented without guaranty and warranty or responsibility any kind, express or limited. Statement or suggestion concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendation to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required

P.O. Box 3, Kibutz Einat 4880500 Israel politiv@politiv.co.il
+972-3-9016060 +972-3-9016040 www.politiv.co.il