TECHNICAL PRODUCT INFORMATION

Product:	Everest diffused thermic Anti-Dust 30% shade
Catalog Number:	E2449
Product description:	Multi-layer polyethylene film. The film contains special additives that block the NIR irradiation during the day to reduce the temperature at the tunnels and greenhouses during the day, thermic (IR) ingredients to reduce heat loss at night and Anti-Dust to minimize the dust on the film
UV Resistance:	2 years at 160-180Kly, 3 years at 120-140 Kly
Thickness:	150-200 µ
Width:	1Up to 18.0 m
Length:	According to customer order

Product properties

Property	Test Method	Units	Value
Tensile Strength at break [MD]	ASTM D-882	MPa.	27
Tensile Strength at break [TD]	ASTM D-882	MPa.	27
Elongation at break [MD]	ASTM D-882	%	600min
Elongation at break [TD]	ASTM D-882	%	600min
Tear resistance [MD]	ASTM D-1922	Kg./mm	10.0
Tear resistance [TD]	ASTM D-1922	Kg./mm	11.0
Falling Dart Impact (200µ)	ASTM D-1709	gr.	>1000
Light transmission	EN 13206	%	80%
Light diffusion	EN 13206	%	65
Thermicity	EN 13206	%	65
UV blocking (320-380 nm)	Internal	%	96
Thickness average tolerance	EN 13206	%	±5% on nominal

All statements, information and data given herein are believed to be accurate a reliable, but are presented without guaranty and warranty or responsibility any kind, express or limited. Statement or suggestion concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendation to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required

P.O. Box 3, Kibutz Einat 4880500 Israel
politiv@politiv.co.il
+972-3-9016060
+972-3-9016040
www.politiv.co.il

Use and limitation:

- **Exposure to chemicals**: exposure of greenhouse films to severe chemical conditions has an adverse effect on the lifetime of the film. Avoid excessive use of agrochemicals such as pesticides, herbicides, fungicides and fertilizers. Take measures to prevent direct contact of chemicals to the film. Ensure that metal structures are galvanized and are free from corrosion. When wooden structure parts are used, avoid contact of the film with resin, oil, petroleum or volatile preservatives. Prevent contact of the film with PVC accessories. Chemicals containing halogens, sulfur, copper, iron, are known to accelerate the degradation of greenhouse films.

  Specifically, if the following elements are found at levels higher than specified, the films are excluded from this warranty:

  Sulfur: max 400 ppm, Chlorine: 40 ppm, Iron: 50 ppm

- **Overheating**: the film has an adverse effect on its lifetime. Hot air should be directed away from the film.

- **Disinfection chemical use**: when chemicals are used to disinfect the soil, the treated soil must be covered with a film for a minimum of three weeks. After the film is removed, the greenhouse should be ventilated.

All statements, information and data given herein are believed to be accurate a reliable, but are presented without guaranty and warranty or responsibility any kind, express or limited. Statement or suggestion concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendation to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required

P.O. Box 3, Kibutz Einat 4880500 Israel politiv@politiv.co.il
+972-3-9016060 +972-3-9016040 www.politiv.co.il